

Test Report

Client: PPG Deco Polska Spolka z o.o.
ul. Kwidzynska 8
51-416 Wroclaw
Poland

Order-No. (Client):

Order-No. (MPA): **902 1447 000-3 /Whr/Scz**

Test Item: **„Domalux Professional Poliuretan Aqua 1S Polmat“**

Specification Applied: DIN V 18032-2:2001-04

Date of Receipt of Test Item 22.02.2011

Date of Test: beginning 01.03.2011

Date of Report: 21.03.2011

Page 1 of 3 text pages

Enclosures :

Supplements:

Total Number of Pages: 3

Number of Reports: 1

The test results relate only to the items tested.

Publication of this report in full or partly is only allowed with written authorization by MPA University of Stuttgart.

In compliance with DIN EN ISO/IEC 17025 accredited Testing Laboratory recognized by DAkkS Deutsche Akkreditierungsstelle GmbH.
Accreditation valid for testing methods listed in the certificates (Reg. No. D-PL-11016-00).

1 Purpose of investigation

You commissioned us to test the sliding properties according to DIN V 18032-2:2001-04 of the floor lacquer "**Domalux Professional Poliuretan Aqua 1S Polmat**" on parquet. For the test we received a sample with the dimensions 0,6 m x 0,2 m on the 22.02.2011.

2 Testing procedure

The test was carried out according to DIN V 18032-2:2001-04.

The procedure applied is accredited according to DIN EN ISO/IEC 17025:2005 (DAkkS registration-no. D-PL-11016-01-09).

Testing conditions: 23-50-2 according to DIN 50014.

3 Test results

The following test results were obtained.

Table 1: Test results:

testing spot no.	sliding coefficient μ
1	0,40
2	0,41
3	0,40
4	0,41
5	0,41

4 Evaluation

According to DIN V 18032-2:2001-04 the following requirement is valid: μ min. 0,4, μ max.

This requirement was fulfilled by the tested floor lacquer

„Domalux Professional Poliuretan Aqua 1S Polmat on parquet.

Prepared by



Norbert Schulz
Tester



Approved and released by



Dipl.-Ing. Rainer Wellhäußer
Vice Section leader