



Investigation Report

Client: PPG Deco Polska Spolka z o. o.
ul. Kwidzyska 8
51-416 Wrocław
Poland

Order-No. (Client):

Order-No. (MPA): **902 4273 000-04/Scz/Whr**

Test Item: **Domalux Professional Poliuretan Aqua 1S półmat**

Specification Applied: EN 13036-4

Date of Receipt of Test Item 05.07.2012

Date of Test: beginning 06.07.2012

Date of Report: 20.07.2012

Page 1 of 3 text pages

Enclosures :

Supplements:

Total Number of Pages: 3

Number of Reports: 1

The test results relate only to the items tested.

Publication of this report in full or partly is only allowed with written authorization by MPA University of Stuttgart.

1 Purpose of investigation

You commissioned us to test the friction of the lacquer "**Domalux Professional Poliuretan Aqua 1S pólmat**" according to EN 13036-4.

For the test we got two sample with the following dimensions 0,2 m x 0,7 m.

2 Testing procedure

The test was carried out according EN 13036-4.

The procedure applied is accredited according to DIN EN ISO/IEC 17025:2005 (DAkkS-registration- no. D-PL-11016-01-09).

Testing conditions: 23-50-2 according to DIN 50014.

3 Test results

The following test results were obtained.

Table 1: Test results

testing spot no.	friction
1	89
2	92
3	92
4	91
5	95
Mean	92

4 Evaluation

Basis for the evaluation are the requirements of EN 14904 for friction of mean (80 – 110), range (+/- 4 units). With a mean value of 92 and a range of - 3 / + 3 units this requirement was fulfilled by the lacquer "**Domalux Professional Poliuretan Aqua 1S pólmat**".

Prepared by

N. Schulz
Norbert Schulz
Tester



Approved and released by

R. Wellhäuser
Dipl.-Ing. Rainer Wellhäuser
Vice Section leader